



SCHEDA TECNICA

MAGIC WHITE

	Metodo											
GRAMMATURA	g/m2	ISO 536	90	100	120	140	160	200	250	300	350	400
GRADO DI BIANCO	%	ISO 11475	169	169	169	169	169	169	169	169	169	169
OPACITA'	%	ISO 2471	92	93	94	95	-	-	-	-	-	-
LISCIATURA	ml/min	ISO 8791-2	80	80	80	80	80	80	80	80	80	80
UMIDITA'	%	ISO 287	5,5	5,5	6	6,5	6,5	6,5	6,5	6,5	6,5	6,5
SPESSORE	µm	ISO 534	103	114	132	155	176	216	268	318	368	420
VOLUME	cm ² /g	ISO 534	1,14	1,14	1,1	1,11	1,1	1,08	1,07	1,06	1,05	1,05