



## TECHNICAL DATA SHEET

### GMUND MOONLIGHT

#### Glance 1 sided | 125 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	112 - 128
Caliper	ISO 534, μm:	175 ± 20
Bulk	ISO 534, cm <sup>3</sup> /g:	1.45 ± 0.1
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 4000
	length, m:	≥ 5000
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 700
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	15 ± 8
	Backside, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	writable

August 27, 2024 DC  
substitutes May 28, 2024



## TECHNICAL DATA SHEET

### GMUND MOONLIGHT

#### Glance 1 sided | 245 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	228 - 262
Caliper	ISO 534, μm:	360 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.45 ± 0.2
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3000
	length, m:	≥ 3500
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	15 ± 8
	Backside, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	writable

August 27, 2024 DC  
substitutes May 28, 2024



## TECHNICAL DATA SHEET

### GMUND MOONLIGHT

#### Glance 1 sided | 355 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	325 - 375
Caliper	ISO 534, μm:	530 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.45 ± 0.2
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3000
	length, m:	≥ 3500
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2500
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	15 ± 8
	Backside, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	writable

August 27, 2024 DC  
substitutes May 28, 2024