



TECHNICAL DATA SHEET

GMUND WOOD

Veneer | 300 g/m²

Grammage	ISO 536, g/m ² :	279 - 321
Caliper	ISO 534, μm:	380 ± 30
Bulk	ISO 534, cm ³ /g:	1.2 ± 0.2
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2700
	length, m:	≥ 3600
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1200
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	15 ± 10
	Backside, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

Veneer | 350 g/m²

Grammage	ISO 536, g/m ² :	326 - 375
Caliper	ISO 534, μm:	430 ± 30
Bulk	ISO 534, cm ³ /g:	1.2 ± 0.2
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3000
	length, m:	≥ 3500
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2000
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	15 ± 10
	Backside, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

Veneer | 500 g/m²

Grammage	ISO 536, g/m ² :	465 - 535
Caliper	ISO 534, μm:	600 ± 60
Bulk	ISO 534, cm ³ /g:	1.2 ± 0.2
Ash	DIN 54370, %:	> 3
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	15 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

Solid | 300 g/m²

Grammage	ISO 536, g/m ² :	279 - 321
Caliper	ISO 534, μm:	390 ± 30
Bulk	ISO 534, cm ³ /g:	1.3 ± 0.15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2800
	length, m:	≥ 3600
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1500
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

Solid | 350 g/m²

Grammage	ISO 536, g/m ² :	326 - 375
Caliper	ISO 534, μm:	470 ± 30
Bulk	ISO 534, cm ³ /g:	1.3 ± 0.15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2250
	length, m:	≥ 2500
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2000
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

Solid | 500 g/m²

Grammage	ISO 536, g/m ² :	465 - 535
Caliper	ISO 534, μm:	620 ± 60
Bulk	ISO 534, cm ³ /g:	1.2 ± 0.2
Ash	DIN 54370, %:	> 3
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



TECHNICAL DATA SHEET

GMUND WOOD

VENEER | SOLID

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Abura	6
Imbuya	4
Chacate	6
Limba	4 - 5
Bubinga	4 - 5
Tindalo	3
Abachi	3
Panga	3 - 4
Gingko	2 - 3