



## TECHNICAL DATA SHEET

### GMUND BIO CYCLE

#### Rag - Baumwolle | 120 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	115 - 128
Caliper	ISO 534, μm:	190 ± 20
Bulk	ISO 534, cm <sup>3</sup> /g:	1.55 ± 0.15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 4000
	length, m:	≥ 5000
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1000
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	30 ± 10
pH-Value	DIN 53124:	≥ 7.5



## TECHNICAL DATA SHEET

### GMUND BIO CYCLE

#### Rag - Baumwolle | 300 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	279 - 321
Caliper	ISO 534, μm:	460 ± 20
Bulk	ISO 534, cm <sup>3</sup> /g:	1.6 ± 0.15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2400
	length, m:	≥ 3000
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2000
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	40 ± 10
pH-Value	DIN 53124:	≥ 7.5

# GMUND



## TECHNICAL DATA SHEET

### GMUND BIO CYCLE

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Rag - Baumwolle

6 - 7

All data refer to our own, in-house conducted measurement results and practical experiences. According to CEPAC, all tolerances specified in the general conditions of sale are to be regarded as fulfilled if 95% of the measured values lie within the prescribed tolerances. Binding for the delivery of our products are the General Conditions of Sale of Paper and Board Manufacturers in EC (CEPAC guideline). We reserve the right for changes to this material due to technical advancement. The use of different measurement devices may lead to deviant measurement results.

October,09. 2023 DC  
substitutes May ,15 2018