



## TECHNICAL DATA SHEET

### GMUND COTTON | 100% Cotton

#### Cotton | 110 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	106 - 114
Caliper	ISO 534, µm:	185 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.75 ± 0.3
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2500
	length, m:	≥ 3000
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 600
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5
Writing with ink	DIN 53126:	o. k.



## TECHNICAL DATA SHEET

### GMUND COTTON | 100% COTTON

#### Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Linen Cream	6 - 7
Max White	4 - 5
Shiny Cream	6 - 7
Natural Beige	7
New Grey	7
Gentlemen Blue	7
Power Blue	5 - 6