GMUND



TECHNICAL DATA SHEET

GMUND 925 two sided

Light Silver | 145 g/m²

Ash DIN 54370, %: > 3

Tensile Index ISO 1924-2:

mean value, length and cross, m: ≥ 3000

length, m: ≥ 5500

cross, m: ≥ 3500

Tear Index, Elmendorf method ISO 1974:

mean value, length and cross, mN: ≥ 500

Dennison-Waxtest US D2482-66T: ≥ 12

Water Absorption ISO 535:

Cobb 60, g/m²: 15 ± 10

pH-Value DIN 53124: ≥ 7.5





TECHNICAL DATA SHEET

GMUND 925 two sided

Silver Pigments | Aqua Silver | Black Silver | 290 g/m²

Grammage ISO 536, g/m²: 270 - 310

Caliper ISO 534, μ m: 310 \pm 30

Bulk ISO 534, cm³/g: 1.1 ± 0.2

Ash DIN 54370, %: > 3

Tensile Index ISO 1924-2:

mean value, length and cross, m: ≥ 4000

length, m: ≥ 5000

cross, m: ≥ 3000

Tear Index, Elmendorf method ISO 1974:

mean value, length and cross, mN: ≥ 1500

Dennison-Waxtest US D2482-66T: ≥ 12

Water Absorption ISO 535:

Cobb 60, g/m²: 15 ± 10

pH-Value DIN 53124: ≥ 7.5

GMUND



TECHNICAL DATA SHEET

GMUND 925 one sided

White Silver | Light Silver | Golden Silver | Brown Silver | 310 g/m²

Grammage ISO 536, g/m²: 288 - 332

Caliper ISO 534, μ m: 370 \pm 30

Bulk ISO 534, cm³/g: 1.1 ± 0.2

Ash DIN 54370, %: > 3

Tensile Index ISO 1924-2:

mean value, length and cross, m: ≥ 3500

length, m: ≥ 4500

cross, m: ≥ 2500

Tear Index, Elmendorf method ISO 1974:

mean value, length and cross, mN: ≥ 1800

Dennison-Waxtest US D2482-66T: ≥ 12

Water Absorption ISO 535:

Cobb 60, g/m²: 15 ± 10

Backside, g/m²: 35 ± 10

pH-Value DIN 53124: ≥ 7.5





TECHNICAL DATA SHEET

GMUND 925

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

White Silver	4 - 5
Light Silver	6
Silver Pigments	6 - 7
Golden Silver	6
Aqua Silver	6
Brown Silver	6 - 7
Black Silver	6 - 7