



## TECHNICAL DATA SHEET

### GMUND ACTION

#### Go to Hell Black | 300 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	279 - 321
Caliper	ISO 534, μm:	400 ± 40
Bulk	ISO 534, cm <sup>3</sup> /g:	1.2 ± 0.15
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2800
	length, m:	≥ 3600
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5



## TECHNICAL DATA SHEET

### GMUND ACTION

Alpine Sparkling Water | Crystal Vanilla Sorbet | Nuclear Acid | Clear Sky Blue |

Night Offshore Blue | Pastel Heart Attack | Dark Silver Cloud |

**310 g/m<sup>2</sup>**

Grammage	ISO 536, g/m <sup>2</sup> :	288 - 332
Caliper	ISO 534, µm:	350 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.2 ± 0.15
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3050
	length, m:	≥ 3600
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	15 ± 10
	Backside, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5

August 01, 2024 DC  
Substitutes October 2022



## TECHNICAL DATA SHEET

### GMUND ACTION

#### Vibrant Arsenic | Electric Blood | 430 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	400 - 460
Caliper	ISO 534, μm:	510 ± 40
Bulk	ISO 534, cm <sup>3</sup> /g:	1.2 ± 0.15
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 3500
	length, m:	≥ 4500
	cross, m:	≥ 2500
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2500
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	15 ± 10
pH-Value	DIN 53124:	≥ 7.5

August 12, 2024 DC  
Substitutes 21. June 2018



## TECHNICAL DATA SHEET

### GMUND ACTION

#### Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Alpine Sparkling Water	5 - 6
Crystal Vanilla Sorbet	6 - 7
Nuclear Acid *	2 - 3
Vibrant Arsenic *	2 - 3
Clear Sky Blue	6
Night Offshore Blue	5 - 6
Pastel Heart Attack *	2
Elektric Blood *	2
Dark Silver Cloud	6
Go to Hell Black	6 - 7

**\*The special colour pigments in the neon colours have a reduced light fastness. Especially direct sunlight will harm them and change the paper colour.**

August 12, 2024 DC  
Substitutes 21. June 2018