



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Tangerine | 240 g/m²

Grammage	ISO 536, g/m ² :	228 - 252
Caliper	ISO 534, μm:	340 ± 25
Bulk	ISO 534, cm ³ /g:	1,4 ± 0,15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2700
	length, m:	≥ 3600
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1400
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7,5



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Coin | 250 g/m²

Grammage	ISO 536, g/m ² :	233 - 257
Caliper	ISO 534, μm:	290 ± 25
Bulk	ISO 534, cm ³ /g:	1,2 ± 0,15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2700
	length, m:	≥ 3600
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1400
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	15 ± 10
	Backside, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7,5



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Snow / Alabaster / Peanut / Pebble / Lipstick /Coal | 300 g/m²

Grammage	ISO 536, g/m ² :	285 - 315
Caliper	ISO 534, μm:	400 ± 25
Bulk	ISO 534, cm ³ /g:	1,4 ± 0,15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2600
	length, m:	≥ 3400
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7,5



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Silver | 310 g/m²

Grammage	ISO 536, g/m ² :	290 – 320
Caliper	ISO 534, µm:	360 ± 25
Bulk	ISO 534, cm ³ /g:	1,4 ± 0,15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2600
	length, m:	≥ 3400
	cross, m:	≥ 1800
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1800
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	15 ± 10
	Backside, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7,5



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Night / Mocha / Peacock | 350 g/m²

Grammage	ISO 536, g/m ² :	332 - 368
Caliper	ISO 534, μm:	480 ± 30
Bulk	ISO 534, cm ³ /g:	1,4 ± 0,15
Ash	DIN 54370, %:	> 3
Tensil Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2800
	length, m:	≥ 3300
	cross, m:	≥ 2300
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2300
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m ² :	35 ± 10
pH-Value	DIN 53124:	≥ 7,5



TECHNICAL DATA SHEET

GMUND LEATHER | HEATHER

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

Snow	4 - 5
Alabaster	6 - 7
Peanut	3
Pebble	6
Silver	7
Coin	7
Night	4
Tangerine	3
Lipstick	2 - 3
Coal	6 - 7
Mocha	4
Peacock	5