



## TECHNICAL DATA SHEET

### GMUND

#### No Color | 120 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	115 - 125
Caliper	ISO 534, μm:	180 ± 20
Bulk	ISO 534, cm <sup>3</sup> /g:	1.5 ± 0.15
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 4000
	length, m:	≥ 5000
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 700
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5

The use of undyed raw material comes with a natural color and brightness variance.



## TECHNICAL DATA SHEET

GMUND

No Color | 300 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	285 - 315
Caliper	ISO 534, μm:	440 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.5 ± 0.15
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2800
	length, m:	≥ 3600
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 2000
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	35 ± 10
pH-Value	DIN 53124:	≥ 7.5

The use of undyed raw material comes with a natural color and brightness variance.



## TECHNICAL DATA SHEET

### GMUND

#### No Bleach | 120 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	115 - 125
Caliper	ISO 534, µm:	180 ± 30
Bulk	ISO 534, cm <sup>3</sup> /g:	1.5 ± 0.2
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 4000
	length, m:	≥ 5000
	cross, m:	≥ 3000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 1000
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	30 ± 10
pH-Value	DIN 53124:	≥ 7.5

The use of undyed raw material comes with a natural color and brightness variance.



## TECHNICAL DATA SHEET

### GMUND

#### No Bleach | 300 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	285 - 315
Caliper	ISO 534, µm:	440 ± 40
Bulk	ISO 534, cm <sup>3</sup> /g:	1.5 ± 0.2
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2800
	length, m:	≥ 3600
	cross, m:	≥ 2000
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 4000
Dennison-Waxtest	US D2482-66T:	≥ 12
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	30 ± 10
pH-Value	DIN 53124:	≥ 7.5

The use of undyed raw material comes with a natural color and brightness variance.

# GMUND



## TECHNICAL DATA SHEET

### GMUND No Color No Bleach

Test of the light-fastness of the color under a xenon arc lamp

Heraeus, Suntest CPS

Evaluation according to the blue scale (wool scale) | DIN EN ISO 105-B02

No Color      6 - 7

No Bleach     3 - 4

All data refer to our own, in-house conducted measurement results and practical experiences. According to CEPAC, all tolerances specified in the general conditions of sale are to be regarded as fulfilled if 95% of the measured values lie within the prescribed tolerances. Binding for the delivery of our products are the General Conditions of Sale of Paper and Board Manufacturers in EC (CEPAC guideline). We reserve the right for changes to this material due to technical advancement. The use of different measurement devices may lead to deviant measurement results.

November 18, 2022 DC  
substitutes July 2016