



ENDURO ICE 80

matt 6938, 79 g/m²

Tear-resistant translucent paper. Ideal for tear-resistant, translucent envelopes, banners, durable inserts, document sleeves or outer packaging with barrier function.

ENDURO Ice 80 is a unique composite material consisting of a 50 µm PP film core and wafer-thin, white natural paper surfaces. The three-layer product structure is durable, resistant to edge tearing and water impermeable. It gives all ENDURO Ice grades identical translucency with an elegant feel and a finely ribbed appearance. This enables applications in areas where conventional translucent papers reach their limits by comparison. It can be cut, punched, perforated, drilled, embossed, scored, folded, glued and bound without issue. Also suitable for hot foil stamping.

The high-quality paper surfaces offer optimized feed properties and printing results. Thanks to the slightly absorbent surface, all common standard inks and varnishes can be used with thin ink application in offset printing. For more challenging layouts with higher colour saturation, we recommend printing inks with oxidative drying or UV-reactive inks. Suitable for laser printing and printing on HP Indigo sheet-fed printing systems, taking our processing instructions into account.

Advantages

- Elegant transparency
- Natural feel
- Tear-resistant
- High fold strength
- Water impermeable
- Excellent printability
- PVC-free



Technologies



General tips

For quality reasons ENDURO should be stored originally packed. Storage & converting conditions of 20±5°C and 50±10% rel. humidity are recommended.

Food contact

Please inform us whenever intended use is linked to food contact.

It may be possible to provide a Declaration of Compliance confirming material suitability for your specific application.

Waste disposal

Due to the film content of over 50%, paper recycling is not recommendable for this product. Smaller quantities can be disposed of together with household waste. ENDURO Ice 80 is considered commercial waste similar to household waste. It is biologically neutral when landfilled.

In most cases, incineration with energy recovery is the most efficient solution from an economic and ecological point of view.

Larger quantities should be disposed of in accordance with local and national regulations. We recommend enquiring with the responsible waste disposal company.

Physical data

Name	Value	Tolerance	Norm
Weight [g/m ²]	79	±6	ISO 536
Thickness (total) [µm]	98	±7	ISO 534
Bending stiffness MD [mN]	> 80		ISO 2493-1; 15°/10mm
Bending stiffness CD [mN]	> 40		ISO 2493-1; 15°/10mm
Tensile strength MD [N/15mm]	> 60		ISO 1924-3/2/300
Tensile strength CD [N/15mm]	> 180		ISO 1924-3/2/300
ISO Brightness, front side [%]	> 70		ISO 2470-1
ISO Brightness, reverse side [%]	> 70		ISO 2470-1
Whiteness, CIE, D65/10°, front side	> 55		ISO 11475
Whiteness, CIE, D65/10°, reverse side	> 55		ISO 11475
Transparency [%]	> 60		DIN 53147

Durability

Originally packed under recommended storage conditions ENDURO rolls and sheets can be stored for at least 3 years.

Printing instructions

Detailed recommendations for printing and processing of ENDURO can be found under Download.