


Digipro Satin

Grammatura	ISO 536	g/m ²	115	130	150	170	200	250	300	350
Spessore	ISO 534	µm	94	107	124	141	168	225	282	346
Volume	ISO 534	cm ³ /g	0,82	0,82	0,83	0,83	0,84	0,90	0,94	0,99
Bianco CIE	ISO 11475	%	127	127	127	127	127	127	127	127
Opacità	ISO 2471	%	94,5	95	96,5	97,5	98	98,5	99	99,5
Lucido carta	ISO 8254-1	%	38	38	38	38	38	38	38	38
Codice di riciclo		PAP	22	22	22	22	21	21	21	21