

Magic Black

Grammatura	ISO 536	g/m ²	350	400	500
Spessore	ISO 534	μm	428	495	610
Volume	ISO 534	cm ³ /g	1,22	1,24	1,22
Umidità	ISO 287	%	7,0	7,0	7,0
Ruvidezza	ISO 8791-2	ml/min	260±50	260±50	400±100
Rigidità Long.	ISO 2493-1	% 15°/50 mm	230	400	800
Rigidità Trasv.	ISO 2493-1	g/m ² 15°/50 mm	130	200	400
Codice di riciclo		PAP	21	21	21



Il marchio della
gestione forestale
responsabile