


West Kote

Grammatura	ISO 536	g/m ²	250	300	350
Spessore	ISO 534	µm	315	387	450
Volume	ISO 534	cm ³ /g	1,3	1,3	1,3
Bianco CIE	ISO 11475	%	111	111	111
Luminosità UV	ISO 2470	%	84	84	84
Lucido 20°	ISO 2813	%	45	45	45
Umidità	ISO 287	%	5,5	5,5	5,5
Rigidità L&W	ISO 2493	mN 15°/50 mm	140/70	240/120	400/200
Codice di riciclo		PAP	21	21	21



Il marchio della
gestione forestale
responsabile