


Performa White™

Fully coated CTMP board with light pigment-coated reverse

Performa White is a coated GC1 board with a three-layer fibre construction and CTMP (chemithermomechanical pulp) in the middle layer. It is triple-pigment-coated on the top side, with one layer of pigment coating on the reverse side. Performa White is also available hard-sized (HS).



Issued: 11.2024 Cancels: 11.2023

Technical specification

| Property/ Unit | Tolerance | | | | | | | | | | | | | Standard |
|---|-------------------|------|--|------|------|------|------|----------|------|------|------|------|-------|------------|
| Grammage, g/m ² | ±4% | 180 | 200 | 220 | 240 | 260 | 280 | 300 | 315 | 325 | 350 | 370 | 400 | ISO 536 |
| Thickness, µm | ±5% | 255 | 295 | 325 | 365 | 400 | 440 | 475 | 505 | 535 | 585 | 625 | 675 | ISO 534 |
| Bending resistance L&W 15° MD, mN | -15% | 108 | 160 | 201 | 265 | 353 | 445 | 535 | 608 | 690 | 800 | 900 | 1080 | - ISO 2493 |
| Bending resistance L&W 15° CD, mN | -15% | 53 | 73 | 92 | 120 | 160 | 202 | 243 | 276 | 290 | 370 | 410 | 500 | |
| Bending moment Taber 15° MD, mNm | -15% | 5.2 | 7.7 | 9.7 | 12.8 | 17.0 | 21.5 | 25.8 | 29.3 | 33.3 | 38.6 | 43.5 | 52.2 | |
| Bending moment Taber 15° CD, mNm | -15% | 2.6 | 3.5 | 4.4 | 5.8 | 7.7 | 9.8 | 11.7 | 13.3 | 14.0 | 17.9 | 19.8 | 24.2 | |
| Bending stiffness DIN 5° MD, mNm | -15% | 8.2 | 14.3 | 18.2 | 24.4 | 33.7 | 43.0 | 51.3 | 59.1 | 66.8 | 78.7 | 91.7 | 109.8 | |
| Bending stiffness DIN 5° CD, mNm | -15% | 4.4 | 6.5 | 8.3 | 11.5 | 14.3 | 18.3 | 22.4 | 25.9 | 30.9 | 35.9 | 42.7 | 51.5 | |
| Moisture, % | ±1, ±1.5 * | 6.2 | 7.0 | 7.0 | 8.0 | 8.1 | 8.3 | 8.6 | 8.7 | 8.7 | 8.9 | 9.1 | 9.3 | ISO 287 |
| ISO Brightness C/2°, %, Top | min. 87 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | 90 | ISO 2470-1 |
| ISO Brightness C/2°, %, Reverse | min. 85 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | 88 | |
| Brightness D65/10°, %, Top | | 97 | 97 | 97 | 97 | 97 | 97 | 97 | 97 | 97 | 97 | 97 | 97 | ISO 2470-2 |
| CIE Whiteness D65/10°, Top | | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | 120 | ISO 11475 |
| CIE Whiteness D65/10°, Reverse | | 114 | 114 | 114 | 114 | 114 | 114 | 114 | 114 | 114 | 114 | 114 | 114 | |
| L*, Top | | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | 95.0 | ISO 5631-2 |
| a*, Top | | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | 1.7 | |
| b*, Top | | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | -7.2 | |
| Surface Smoothness, PPS 10, µm, Top | max. 1.7 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | 1.0 | ISO 8791-4 |
| Surface Smoothness, PPS 10, µm, Reverse | max. 8.4, 9.0 *** | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 150 6/91-4 |
| Gloss 75°, % | | 45 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | ISO 8254-1 |
| Scott Bond, J/m² | min. 100 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | 145 | TAPPI 569 |
| Edge wicking**, kg/m² | max. 1.0 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | |
| Cobb 60, g/m², Top | max. 60 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | ISO 535 |
| Cobb 60, g/m², Reverse | max. 60 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | 30 | |
| Robinson chocolate test | | | max 0.5 for one year storage in reels/pallet | | | | | EN1230-2 | | | | | | |

*) For 325 – 400 g/m²

**) For Hardsized

***) For 300-400 g/m²





Performa White™

Fully coated CTMP board with light pigment-coated reverse

Certificates

Quality management ISO 9001
Environmental management ISO 14001
Product safety FSSC 22000
Occupational health and safety ISO 45001
Energy management ISO 50001
EU Ecolabel standard contract FI/011/002, fulfil the ecological criteria for Graphic Paper, (EU) 2019/70, L15/27 (17.1.2019).





FSC and PEFC certified board available upon request.



EU Ecolabel: FI/011/002

The EU Ecolabel confirms that the board fulfils the European Commission's ecological criteria for copying and graphic paper and is therefore only available for graphical end uses. EU Ecolabel available upon request on graphical end uses.



Paperboard can be recycled

Key characteristics and main enduses

Performa White is an aesthetically appealing board that combines performance with a beautiful white appearance. This board is ideal for chocolate, confectionery and cosmetic packaging, as well as for graphical end uses, including the most demanding finishing effects. Thanks to the triple-pigment-coated top side, Performa White gives a very good print result, and the reverse side is also suitable for full-colour printing. The high brightness and whiteness contribute to optimal visual appearance.

Printing and finishing techniques

The product can be used with different printing techniques such as offset, flexo, rotogravure and digital printing. In digital printing, the product is suitable for several different sheet- or web-fed presses. Inkjet, dry or liquid toner technology can be used, although in some cases, pretreatment of the substrate might be required. The latest certification status can be verified on the press manufacturer's website or with local Stora Enso representatives. It is important to check the limitations of the equipment, particularly because of the exceptional difference in the thickness and stiffness of board compared with paper in the same grammages. When running thicker substrates, the press manufacturer's recommendations should be referred to for optimal grain direction. Essentially all of the same finishing processes apply to both digitally printed and offset printed work. Since a wide variety of digital printing equipment is available in the market, it is important that a new commercial print job is always preceded by a trial run, including all required printing and converting process phases. The product works very well with different finishing techniques, such as embossing, hot foil stamping and others. It is suitable for laser coding and ink jet marking. Certificates according to PTS-DF 105/2019 and PTS-DF 103/2022 are available upon request.

Storage recommendations

For optimal printing results, the moisture proof wrapping should not be removed until the board has reached the temperature of the press room.

| Pallet/Reel Weight (kg) | Difference in temperature between board and press room (press room temp. approx. 20°C) | | | | | | | |
|----------------------------|--|--------|--------|--|--|--|--|--|
| | 10°C | 20°C | 30°C | | | | | |
| 400 kg | 2 days | 2 days | 3 days | | | | | |
| 800 kg | 2 days | 3 days | 4 days | | | | | |
| 1200 kg | 2 days | 4 days | 5 days | | | | | |

The product properties, according to the specifications, are guaranteed for 12 months after the production date. In order to ensure product safety, the product must be well wrapped and stored in its original cover indoors, sheltered from rain and snow. The recommended storage conditions are 50–55% relative humidity and 20–23°C.

